

AMENDMENTS TO THE SPECIFICATION


Page 8, after the paragraph numbered 17, please insert:

18. A polymer cell according to any one of the items 14-17, wherein an amount of the polymer to a total amount of the polymer and the support salt is 80-95% by mass.

19. A polymer cell according to any one of the items 14-18, wherein the electrolyte further contains a phosphazene derivative and/or an isomer of a phosphazene derivative.

Please amend the paragraph bridging pages 8 and 9 as follows:

~~18-20.~~ A polymer cell according to ~~any one of the items 14-18~~ the item 19, wherein the phosphazene derivative has a viscosity at 25°C of not more than 300 mPa · s (300 cP) and is represented by the following formula (VIII) or (IX):



(wherein R¹, R² and R³ are independently a monovalent substituent or a halogen element, and X¹ is a substituent containing at least one element selected from the group consisting of carbon, silicon, germanium, tin, nitrogen, phosphorus, arsenic, antimony, bismuth, oxygen, sulfur, selenium, tellurium and polonium, and Y¹, Y² and Y³ are independently a bivalent connecting group, a bivalent element or a single bond)



(wherein R⁴ is independently a monovalent substituent or a halogen element, and n is 3-15).